

ADVA® CAST 630N

High Range Water Reducing Admixture

DESCRIPTION

ADVA® CAST 630N is a polycarboxylic high range water-reducing admixture. ADVA® CAST 630N contains no added Chlorides and no TEA.

ADVA® CAST 630N is specially designed for producing superior high early strength concrete in precast applications. ADVA® CAST 630N complies with AS 1478.1-2000, Type HWR.

BENEFITS

- Superior early strength enhancement
- High workability, ideal for precast applications
- Superior water reduction with water content reduced by up to 30%
- Optimise precast concrete production, may remove the need for heat curing to achieve high early strength concrete

APPLICATION

- Low water-cement ratios in low to high slump ranges
- Precast structural elements

INDICATIVE INFORMATION

Product Nature	Liquid
Color	Yellow
Lifetime	12 months
Specific gravity (kg)	1,060 ± 0,020
pH	5,50 ± 0,70

PACKAGING

- Bulk
- IBC 1000L
- 205 L Drum
- Pail

SAFETY

Prior to any use, please read carefully the Safety Data Sheet (SDS).

METHOD OF USE

Dosage :

Dosage rates of ADVA® CAST 630N can vary with type of applications, but normally ranges from 300 to 1,000 ml / 100 kg of cementitious material. In most instances, the dose of 400 to 800 ml / 100 kg of cementitious material is sufficient. Should conditions require using more than recommended dosage rates, please consult your local Chryso representative.

Equipment :

Please contact your local Chryso representative for further information regarding the dispensing equipment for this product.

COMPATIBILITY

- Water reducers or accelerators
- Specialty admixtures like DCI® corrosion inhibitor, Chryso®Eclipse shrinkage-reducing admixture and V-MAR® rheology-modifying admixture
- When using admixtures in combination, each admixture should be added separately to the mix

PRECAUTIONS

- ADVA® CAST 630N contains no flammable ingredients. It will begin to freeze at approximately 0°C, but will return to full strength after thawing and thorough agitation
- In storage, and for proper dispensing, ADVA® CAST 630N should be maintained at temperatures above 0°C