

## ADVA® 555N

New Generation, high range water reducing/  
superplasticizing admixture

### DESCRIPTION

ADVA® 555N is the latest technology in the development of high range water-reducing superplasticizing admixtures. It is an innovative, versatile, third generation polycarboxylic ether polymer. ADVA® 555N is developed for the premix and precast

industries to maximise performance through a wide range of concrete strengths. ADVA® 555N does not contain added chloride or triethanolamine. ADVA® 555N complies with AS 1478.1-2000, Type HWR.

### BENEFITS

- No need for other superplasticizers on specific applications
- Produces very high slump concrete at low water-cement ratios without segregation and loss of strength
- High early strength development with reduced heat energy for curing
- Excellent slump retention properties without retardation
- Can be added at the batch plant, no need for on-site addition
- Requires less vibration for ease of placement in reinforced concrete
- Improves surface and off form finishes

### APPLICATION

- Low water-cement ratio concrete with high placement slumps
- Tremie and pump mixes that require extended slump life
- Precast and prestressed applications for high early strengths and reduced heat energy for curing

### INDICATIVE INFORMATION

|                              |               |
|------------------------------|---------------|
| <b>Product Nature</b>        | Liquid        |
| <b>Color</b>                 | Yellow        |
| <b>Lifetime</b>              | 12 months     |
| <b>Specific gravity (kg)</b> | 1,065 ± 0,005 |
| <b>pH</b>                    | 5,50 ± 0,50   |

### PACKAGING

- Bulk
- IBC 1000L
- 205 L Drum
- Pail

### SAFETY

Prior to any use, please read carefully the Safety Data Sheet (SDS).

### METHOD OF USE

#### Dosage :

Dosage rates of ADVA® 555N can vary depending on the application, However a typical dose range would be between 200 and 600 ml / 100 kgs total cementitious materials. Higher dose rates can be considered for special applications. At a given water-cement ratio, the slump can be controlled by varying the dose rates. It is recommended that trials are conducted beforehand to determine the optimum dose range to suit your application. If further assistance is required, please consult your local Chryso representative.

#### Equipment :

Please contact your local Chryso representative for further information regarding the dispensing equipment for this product.

### COMPATIBILITY

- Portland cements ; fly ash, blast furnace slag, silica fume and limestone blends
- Compatible with V-MAR® 3 ; CONCERA® CP 8600 and most of the concrete admixtures
- When using admixtures in combination, each admixture should be added separately to the mix